



MATERIAL REPORT

REPORT NUMBER: KK2216

DATE: 2/20/98

TITLE: Evaluation of Parker Compound N1239-70

PURPOSE: To obtain general information.

Recommended temperature limits: -25⁰F to 300/325⁰F

Recommended For

Refrigerants

Petroleum based hydraulic oil, motor oil, transmission fluid,
grease

R134a

Water/glycol/steam

HFA, HFB, and HFC fluids

Ozone, aging, and weather resistance

Not Recommended For

Polar solvents (ketones and esters)

Strong acids

Chlorinated hydrocarbons

Auto and aircraft brake fluids



REPORT DATA

Report Number: KK2216

LABORATORY REPORT

<u>Original Physical Properties</u>	<u>Results</u>
Hardness, Shore A, pts	73
Tensile Strength, psi	2672
Elongation, %	278
Modulus @ 100%, psi	875
<u>ASTM D 471, 70 HR @ 302°F ASTM #3</u>	
Hardness Change, pts.	-3
Tensile Change, %	-48.9
Elongation Change, %	-30.2
Modulus Change, %	-31.9
Volume Change, %	+23.1
Compression Set, Test Method	
<u>ASTM D39, Spliced Specimen</u>	
% Deflection, max	20.1
<u>ASTM D 471, 70 hr @ 302°F IRM903.</u>	
Hardness Change, pts	-4
Tensile Strength Change, %	-30.4
Elongation Change, %	-19.1
Modulus Change, %	-18.5
Volume Change, %	+17.7