

## Marco Compound # F1006 40 Durometer, Blue, Commercial Grade Technical Datasheet

### Common Names:

Fluorosilicone, FVMQ

### General Description:

Fluorosilicone is a widely used elastomer that can be compounded to meet a wide range of application conditions. The mechanical and physical properties are very similar to silicone rubber. However, fluorosilicone offers improved fuel and mineral oil resistance but poor hot air resistance when compared with silicone. This material is widely used in semiconductor Ashing equipment for its resistance to oxygen plasma. Please contact [sales@marcorubber.com](mailto:sales@marcorubber.com) for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

### Features:

- Excellent flexibility and resistance to compression set
- Excellent resistance to aging and weather-sunlight
- Resistance to oxidizing chemicals, animal and vegetable oils, fuels, aromatic and chlorinated solvents
- Resistant to diluted alkalies, diester oils, aliphatic and aromatic fluorocarbons, silicone oil, toluene, benzene, ozone and oxidative environments.

### Limitations:

- Brake fluids, ketones, hydrazine, aldehydes, amines, ketones
- Poor abrasion resistance

### Service Temperature:

-100 to 350°F (-73 to 177°C)

### Specification:

ASTM D2000 M2FK406 A19 EF31 EO36

## PHYSICAL PROPERTIES

ORIGINAL PROPERTIES	ASTM D2000 Requirements	Typical Test Results
Hardness, Shore A	40 +/- 5	38
Color	Blue	Blue
Tensile Strength, MPa (psi)	6.0 (870)	7.9 (1146)
Ultimate Elongation	150	447
Specific Gravity	----	1.437

HEAT RESISTANCE – A19, ASTM D 573 (70 hrs. @ 200°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+15	+1
Tensile Strength Change, %, ASTM D412	-45 (max)	-25
Ultimate Elongation Change, %, ASTM D412	-45 (max)	-23

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

<b>COMPRESSION SET – ASTM D 395 Method B (22 hrs. @ 175°C)</b>	<b>ASTM D2000 Requirements</b>	<b>Typical Test Results</b>
Permanent Set %	-----	+10

<b>FLUID RESISTANCE – ASTM Fuel C – EF31, ASTM D 471 (70 hrs. @ 23°C)</b>	<b>ASTM D2000 Requirements</b>	<b>Typical Test Results</b>
Hardness Change, Shore A, ASTM D2240	0 to +15	-5
Tensile Strength Change, %, ASTM D412	-60	-19
Ultimate Elongation Change, %, ASTM D412	-50	-17
Volume Change, %, ASTM D412	0 to +25	+20

<b>FLUID RESISTANCE – ASTM #3 Oil – EO36, ASTM D 471 (70 hrs. @ 150°C)</b>	<b>ASTM D2000 Requirements</b>	<b>Typical Test Results</b>
Hardness Change, Shore A, ASTM D2240	0 to 10	-5
Tensile Strength Change, %, ASTM D412	-35	-17
Ultimate Elongation Change, %, ASTM D412	-30	-27
Volume Change, %, ASTM D412	0 to +10	+3

Date: 2015-08-27

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.