



MATERIAL REPORT

DATE: 04/12/94

TITLE: Evaluation of Parker's Compound NL153-70

CONCLUSION: Compound NL153-70 meets or exceeds all requirements of subject specification.

Recommended Temperature Range: -30 to 250F

Recommended for: petroleum oils, water (up to 180F),
Salt & Alkali solutions, weak acids

Not Recommended for: aromatic fuels, strong acids,
glycols, ozone, polar solvents

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40512
(859) 269-2351

REPORT DATA

<u>Original Physical Properties, ASTM D1414, D2240</u>	<u>NL153-70 Test Results</u>
Hardness, Shore A, pts.	69
Tensile Strength, psi	2200
Ultimate Elongation, %	350
Modulus @ 100%, psi	456
Compression Set, ASTM D395 Method B (70 hrs. @ 257°F)	
% Deflection	39
Dry Heat Resistance, ASTM D573 (70 hrs. @ 250°F)	
Hardness Change, pts.	+9
Tensile Change, %	0
Elongation Change, %	-38
Fluid Immersion, ASTM D471 ASTM #1 Oil, (70 hrs. @ 302°F)	
Hardness Change, pts.	+3
Tensile Change, %	-8
Elongation Change, %	-24
Volume Change, %	-5
Fluid Immersion, ASTM D471 ASTM #3, (70 hrs. @ 302°F)	
Hardness Change, pts.	-5
Tensile Change, %	-10
Elongation Change, %	0
Volume Change, %	+16
Fluid Immersion, ASTM D471 Distilled Water, (70 hrs. @ 212°F)	
Hardness Change, pts.	0
Tensile Change, %	-8
Elongation Change, %	-12
Volume Change, %	0
Low Temperature Brittleness, ASTM D1329	
TR-10, °F	-10