

Marco Compound # V1004

90 Durometer, Black, Per AMS-7259 and Mil-R-83248C

Technical Datasheet

Common Names:

FKM, Fluoropolymer, Fluorel®, Viton®,

General Description:

FKM compounds are widely used in chemical, automotive, aerospace and industrial applications. These compounds offer excellent chemical and temperature resistance. There are many additional specialty compounds based on A, B, F, GLT, GFLT, LTFE and ETP polymer types. Please contact sales@marcorubber.com for assistance in selecting a specialized compound when increased resistance to temperature, chemicals, or physical properties is required.

Features:

- High temperature resistance.
- High durometer.
- Excellent resistance to acids, fuels, mineral oils, greases, aliphatic, aromatic and chlorinated hydrocarbons, non-flammable hydraulic fluids (HFD) and many organic solvents and chemicals.
- Excellent resistance to aging and ozone.
- Low gas permeability, low compression set.

Limitations:

- Steam, hot water, polar solvents, low molecular weight organic solvents and glycol-based brake fluids.

Cure System:

Bisphenol

Service Temperature:

-15 to 437°F (-26 to 225°C)

(Additional compounds may available with expanded temperature ranges).

Specification:

AMS-7259 (AS3581) and MIL-R-83248C (M83248) Type 1 Class 2

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	Specification Requirements	Typical Test Results
Hardness, Shore A	90 +/- 5	89
Color	Black	Black
Tensile Strength, psi	1,400min.	1990
Ultimate Elongation, %	100 Min.	121
Specific Gravity, ASTM D297	As determined	1.84

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

TEMPERATURE RETRACTION – ASTM D1329	Specification Requirements	Typical Test Results
TR-10, Degrees F	+ 5 or colder	+3

HEAT RESISTANCE – AIR AGING ASTM D573 (70 hrs. @ 518°F)	Specification Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	-5 to +10	+4
Tensile Strength Change, %, ASTM D1414	-45 (max)	-9
Ultimate Elongation Change, %, ASTM D1414	-20 (max)	+12
Weight Loss, %, ASTM D297	10 max	4

COMPRESSION SET – ASTM D395 Method B and ASTM D1414 (22 hrs. @ 392°C)	Specification Requirements	Typical Test Results
Permanent Set %	25 (max)	12
Percentage of original deflection, %	60 (max)	45

ARM-200 FLUID IMMERSION - ASTM D471 and ASTM D1414 (70 hrs. @ 392°F)	Specification Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	-15 to 0	-10
Tensile Strength Change, %, ASTM D1414	-35 (max)	-14
Ultimate Elongation Change, %, ASTM D1414	-20 (max)	+10
Volume Change, %, ASTM D297	+1 to + 25	+15

COMPRESSION SET – ASTM D395 Method B and ASTM D1414 (70 hrs. @ 392°C) in ARM-200	Specification Requirements	Typical Test Results
Permanent Set, %	20 (max)	8

FUEL B IMMERSION - ASTM D471 and ASTM D1414 (70 hrs. @ 75°F)	Specification Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+/- 5	-1
Tensile Strength Change, %, ASTM D1414	-20 (max)	-8
Ultimate Elongation Change, %, ASTM D1414	-20 (max)	-2
Volume Change, %, ASTM D471	0 to + 5	+1

Date: 2016-10-3

Viton® is a registered trademark of Dupont.

Fluorel® is a registered trademark of Dyneon.