

Marco Compound # V1148

70 Durometer, Black, Metal Detectable, FDA Compliant FKM Technical Datasheet

Common Names:

FKM, Fluoropolymer, Fluorel®, Viton®,

General Description:

FKM compounds are widely used in chemical, automotive, aerospace and industrial applications. These compounds offer excellent chemical and temperature resistance. There are many additional specialty compounds based on A, B, F, GLT, GFLT, LTFE and ETP polymer types. Please contact sales@marcorubber.com for assistance in selecting a specialized compound when increased resistance to temperature, chemicals, or physical properties is required.

Features:

- Metal detectable
- FDA Compliant
- High temperature resistance.
- Excellent resistance to acids, fuels, mineral oils, greases, aliphatic, aromatic and chlorinated hydrocarbons, non-flammable hydraulic fluids (HFD) and many organic solvents and chemicals.
- Excellent resistance to aging and ozone.
- Low gas permeability, low compression set.

Limitations:

- Steam, hot water, amines, polar solvents, low molecular weight organic solvents and glycol-based brake fluids.

Service Temperature:

-15 to 392°F (-26 to +200°C)

TYPICAL PHYSICAL PROPERTIES

ORIGINAL PROPERTIES	ASTM	Value
Hardness, Shore A, ASTM D2240	D1415	74
Color		Black
Tensile Strength, MPa (psi), ASTM D412	D412	9.0 (1,300)
Ultimate Elongation, %, ASTM D412	D412	190
Specific gravity		1.94
Compression Set 22 Hrs @ 200°C, ASTM D395	D395	28%

Date: 2016-10-3

Viton® is a registered trademark of Dupont.

Fluorel® is a registered trademark of Dyneon.

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.