



**Marco Compound # E1037**  
**70 Durometer, White, FDA EPDM**  
**Technical Datasheet**

**Common Names:**

Ethylene-Propylene (EP, EPDM)

**General Description:**

EPDM rubber (ethylene propylene diene monomer rubber) is an elastomer which is characterized by wide range of applications and good chemical resistance.

**Features:**

- FDA compliant
- Good heat and compression resistance.
- Resistant to ketones, hot and cold water, steam, alkalis, polar solvents, ozone, sunlight, alcohols, glycol engine coolant and Skydrol (phosphate ester hydraulic fluid).

**Limitations:**

- Not recommended for oils, gasoline, kerosene, aromatic and aliphatic hydrocarbon, halogenated solvents, concentrated acids, non-polar solvents, petroleum oils and aromatic fuels.

**Cure System:**

- Sulphur

**Service Temperature:**

-55 to 250° F (-54 to 121° C)

**Specification:**

ASTM D2000 M8BA703 A14 B13 F19

**PHYSICAL PROPERTY STANDARDS**

ORIGINAL PROPERTIES	D2000 Specification Requirements	Typical Test Results
Hardness, Shore A	70 +/- 5	69
Color	White	White
Tensile Strength, psi	432	700
Ultimate Elongation, %	150	585
Specific Gravity		1.34

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

HEAT RESISTANCE – A14, ASTM D 865 (70 hrs. @ 100°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points, max.	+/-15	+4
Tensile Strength Change, %, max.	+/-30	+3
Ultimate Elongation Change, %, max.	-50	-26

COMPRESSION SET – B13, ASTM D 395 Method B (22 hrs. @ 70°C)	D2000 Specification Requirements	Typical Test Results
Permanent Set, %, max.	25	23

LOW TEMPERATURE RESISTANCE – F17, ASTM D 2137 Method A, 9.3.2	D2000 Specification Requirements	Typical Test Results
(Non-brittle after 3 min. @ -55°C)	Non-Brittle	Pass

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.