



Marco Compound # E1040

70 Durometer, Red, Peroxide Cured EPDM

Technical Datasheet

Common Names:

Ethylene-Propylene (EP, EPDM)

General Description:

EPDM rubber (ethylene propylene diene monomer rubber) is an elastomer which is characterized by wide range of applications and good chemical resistance. Marco compound E1040 is peroxide cured for increased chemicals resistance.

Features:

- Good heat and compression resistance.
- Resistant to ketones, hot and cold water, steam, alkalis, polar solvents, ozone, sunlight, alcohols, glycol engine coolant and Skydrol (phosphate ester hydraulic fluid).

Limitations:

- Not recommended for oils, gasoline, kerosene, aromatic and aliphatic hydrocarbon, halogenated solvents, concentrated acids, non-polar solvents, petroleum oils and aromatic fuels.

Cure System:

- Peroxide

Service Temperature:

-65 to 300° F (-54 to 150° C)

Specification:

ASTM D2000 M2BA710 A14 B13 F19 Z1 (Z1=PEROXIDE CURE)

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	D2000 Specification Requirements	Typical Test Results
Hardness, Shore A	70 +/- 5	67
Color	Red	Red
Tensile Strength, MPa (psi)	10 (1450)	10.7 (1551)
Ultimate Elongation , %, min.	250	477
Specific Gravity	-----	1.294

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

HEAT RESISTANCE – A13, ASTM D 865 (70 hrs. @ 100°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points, max.	+/-15	+1
Tensile Strength Change, %, max.	+/-30	+0
Ultimate Elongation Change, %, max.	-50	-17

COMPRESSION SET– B13, ASTM D395 Method B (22 hrs. @ 70°C)	D2000 Specification Requirements	Typical Test Results
Permanent Set, %	50	14

LOW TEMPERATURE RESISTANCE – F19, ASTM D 2137 Method A, 9.3.2	D2000 Specification Requirements	Typical Test Results
Non-brittle after 3 min. @ -55°C	Pass	Pass

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.