

Marco Compound # E1097

70 Durometer, Black, FDA, NSF61, 3A, Chloramine Resistant EPDM Technical Datasheet

Common Names:

Ethylene-Propylene (EP, EPDM)

General Description:

EPDM rubber (ethylene propylene diene monomer rubber) is an elastomer which is characterized by wide range of applications and good chemical resistance. Marco compound E1097 meets a variety of specifications for use in food and beverage handling applications.

Features:

- FDA, NSF61, and 3A Sanitary compliant
- Chloramine resistant
- Good heat and compression resistance.
- Resistant to ketones, hot and cold water, steam, alkalis, polar solvents, ozone, sunlight, alcohols, glycol engine coolant and Skydrol (phosphate ester hydraulic fluid).

Limitations:

- Not recommended for oils, gasoline, kerosene, aromatic and aliphatic hydrocarbon, halogenated solvents, concentrated acids, non-polar solvents, petroleum oils and aromatic fuels.

Cure System:

- **Peroxide**

Service Temperature:

-65 to 300° F (-54 to 150° C)

Specification:

ASTM D2000 M4CA710 A25 B35 EA14 F17

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	D2000 Specification Requirements	Typical Test Results
Hardness, Shore A	70 +/- 5	72
Color	Black	Black
Tensile Strength, MPa (psi)	10.0 (1,450)	15.30 (2,200)
Ultimate Elongation, %	125	190
Modulus at 100% elongation, psi	Report	807
Specific Gravity	Report	1.12

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

HEAT AGING – A25, ASTM D 865 (70 hrs. @ 125°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points, max.	10	+2
Tensile Strength Change, %, max.	-20	-2
Ultimate Elongation Change, %, max.	-40	-11

COMPRESSION SET – B35, ASTM D 395 Method B (22 hrs. @ 125°C)	D2000 Specification Requirements	Typical Test Results
Permanent Set, %, max.	70	11

FLUID RESISTENCE, Water – EA14, ASTM D 471 (70 hrs. @ 100°C)	D2000 Specification Requirements	Typical Test Results
Volume Change, %	+/- 5	0.4

LOW TEMPERATURE RESISTANCE – F17, ASTM D 2137	D2000 Specification Requirements	Typical Test Results
Non-brittle after 3 min. @ -40°C	Pass	Pass

TEAR RESISTANCE – D624	D2000 Specification Requirements	Typical Test Results
Die C, Kgf/cm		24

FLUID AGED, Chloramine (100 ppm) – D471, (1344 hrs. @ 60°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points	Report	-4
Tensile Strength Change, %	Report	+12
Ultimate Elongation Change, %, max.	Report	+8
Volume Change, %	Report	+2.7

FLUID AGED, Chloramine (100 ppm) –D471, (1344 hrs. @ 80°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points	Report	-4
Tensile Strength Change, %	Report	+8
Ultimate Elongation Change, %, max.	Report	+7
Volume Change, %	Report	+2

FLUID AGED, Chloramine – D471, (24 hrs. @ 70°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points	Report	-4
Tensile Strength Change, %	Report	+3
Ultimate Elongation Change, %, max.	Report	+0.4
Volume Change, %	Report	+0.7

FLUID AGED, Chloramine – D471, (672 hrs. @ 70°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points	Report	-1
Tensile Strength Change, %	Report	+6
Ultimate Elongation Change, %, max.	Report	
Volume Change, %	Report	

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

FLUID AGED, Tap Water – D471, (24 hrs. @ 100°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points	Report	-4
Tensile Strength Change, %	Report	+7
Ultimate Elongation Change, %, max.	Report	+1.2
Volume Change, %	Report	+1.1

FLUID AGED, Tap Water –D471, (672 hrs. @ 100°C)	D2000 Specification Requirements	Typical Test Results
Hardness Change, points	Report	-4
Tensile Strength Change, %	Report	-3
Ultimate Elongation Change, %, max.	Report	+1.6
Volume Change, %	Report	+1.4

Date: 2016-7-1

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.