



Marco Compound # E1130
70 Durometer, Black, FDA and NSF51 EPDM
Technical Datasheet

Common Names:

Ethylene-Propylene (EP, EPDM)

General Description:

EPDM rubber (ethylene propylene diene monomer rubber) is an elastomer which is characterized by wide range of applications and good chemical resistance.

Features:

- FDA compliant and NSF51 compliant
- Good heat and compression resistance.
- Resistant to ketones, hot and cold water, steam, alkalis, polar solvents, ozone, sunlight, alcohols, glycol engine coolant and Skydrol (phosphate ester hydraulic fluid).

Limitations:

- Not recommended for oils, gasoline, kerosene, aromatic and aliphatic hydrocarbon, halogenated solvents, concentrated acids, non-polar solvents, petroleum oils and aromatic fuels.

Service Temperature:

-65 to 300° F (-54 to 150° C)

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	Typical Test Results
Hardness, Shore A	73
Color	Black
Tensile Strength, MPa (psi)	14 (2030)
Ultimate Elongation, %	300
Tear Resistance, KN/m	34

COMPRESSION SET – ASTM D 395 Method B (70 hrs. @ 150°C)	Typical Test Results
Permanent Set, %, max.	70

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.