



Marco Compound # M1005
65 Durometer, Black, AMS7271 & AS3578 Buna-N
Technical Datasheet

Common Names:

NBR (acrylonitrile butadiene rubber), **Buna-N**, Nitrile.

General Description:

Most commonly used general purpose o-ring material because of relative low cost, good mechanical properties, and basic resistance to many common lubricants. Specific physical and chemical resistances vary by compound formulation. M1005 is formulated to provide value with balance cost and performance. Please contact engineering@marcorubber.com for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

Features:

- Meets AMS7271 & AS3578
- Relative low cost.
- Good/Excellent resistance to compression set and tear/abrasion.
- Good/Excellent resistance to many petroleum oils/greases, hydraulic fluids, alcohol, ambient water, silicone greases, Di-ester base lubricants and ethylene-glycol based fluids.

Limitations:

- Ozone, direct sunlight, UV, weathering, aromatic fuels, glycol-based brake fluids, polar solvents, non-flammable hydraulic fluids (HFD), aromatic/chlorinated hydrocarbons, ketones, esters, and aldehydes, 15 year shelf life.

Cure System:

Sulfur

(Peroxide cured CPDs available with improved physical, chemical, and thermal properties).

Service Temperature:

-70 to 200° F

Specification:

ASTM 2000 M2BG7610 A14 EO14 EO34 F17 Z1

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	ASTM D2000 Requirements	Typical Test Results
Hardness, Shore A	65 +/- 5	63
Color	Black	Black
Tensile Strength, psi	1,450 min.	2,300
Ultimate Elongation, %	300 min.	380

Information within is believed to be accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts supplied in this material will perform satisfactorily in specific applications. It's the customer's responsibility to evaluate prior to use.

HEAT RESISTANCE – A14, ASTM D 573 (70 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points	+/- 15	+7
Tensile Strength Change, %	+/- 30	-2
Ultimate Elongation Change, %	-50 max.	-27

COMPRESSION SET – B14, ASTM D 325 Method B (22 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Permanent Set %	25 max.	7

FLUID RESISTANCE –ASTM #1 Oil – EO14, ASTM D 471 (70 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points	-5 to +10	+1
Tensile Strength Change, %	-25 max.	+10
Ultimate Elongation Change, %	-45 max.	-6
Volume Change, %	-10 to +5	-1

FLUID RESISTANCE – IRM 903 Oil, -EO34, ASTM D 471 (70 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Volume Change, %	+40	+7

LOW TEMPERATURE RESISTANCE – F17, ASTM D 2137 Method A, 9.3.2 (Non-brittle after 3 min. @ -40°C)	ASTM D2000 Requirements	Typical Test Results
	Pass	Pass

Information within is believed to be accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts supplied in this material will perform satisfactorily in specific applications. It's the customer's responsibility to evaluate prior to use.