



MATERIAL REPORT

DATE: October 2000

- TITLE:** General evaluation of Parker Compound FF350-75.
- PURPOSE:** To obtain general data for Parker Compound FF350-75.
- CONCLUSION:** Parker Compound FF350-75 is an ultra high temperature and clean perfluorinated elastomer.

Recommended temperature limits: 5 to 608 °F

Recommended For

Aliphatic and aromatic hydrocarbons
Chlorinated hydrocarbons
Polar solvents (acetone, methylethylketone, dioxane)
Inorganic and organic acids
Water and steam
High vacuum with minimal loss in weight
Petroleum oil
Wet/dry chlorine

Not Recommended For

Fluorinated refrigerants (R11, 12, 13, 113, 114)
Uranium hexafluoride
Molten Metals
Gaseous and alkali metals

**REPORT DATA**

	<u>FF350-75 2-214 O-Rings</u>
<u>Original Physical Properties</u>	
Hardness, Shore A, pts.	74
Tensile Strength, MPa	16.3
Elongation, %, min.	125
Modulus @ 100% Elongation, MPa	9.4
<u>Compression Set, 70 Hrs @ 200°C, ASTM D395 Method B</u>	
Permanent Set, %	13
<u>Compression Set, 70 Hrs @ 260°C, ASTM D395 Method B</u>	
Permanent Set, %	26
<u>Low Temperature Retraction, ASTM D1329</u>	
TR-10 in degrees C	1
<u>Volume Change, 70 Hrs @ RT, ASTM D471</u>	
Acetone, % Volume Change	0.3
Methyl Ethyl Ketone, % Volume Change	0.2
Methanol, % Volume Change	0.2
Benzene, % Volume Change	0.3
Toluene, % Volume Change	0.3
Dichloromethane, % Volume Change	0.5
Chloroform, % Volume Change	0.5
Ethyl Acetate, % Volume Change	0.4
MTBE, % Volume Change	0.3
Glacial Acetic Acid, % Volume Change	0.1
Conc. Phosphoric Acid, % Volume Change	0.1
50/50 by Volume, MEK/Methanol, % Volume Change	0.6
Tetrahydrofuran (THF), % Volume Change	0.4
Styrene Monomer, % Volume Change	0.2
Methyl Methacrylate Monomer, % Volume Change	0.3