



# MATERIAL REPORT

REPORT NUMBER: KK2214

DATE: 2/20/98

**TITLE:** General evaluation of N1219-60.

**PURPOSE:** To provide general information.

**CONCLUSION:** N1219-60 is a NSF51 approved material exhibiting typical physical properties.

**Recommended Temperature Range:** -30 to 225F

**Recommended for:** petroleum oils, water (up to 212F),  
Salt & Alkali solutions, weak acids

**Not Recommended for:** aromatic fuels, strong acids,  
glycols, ozone, polar solvents

Parker O-Ring Division  
2360 Palumbo Drive  
Lexington, Kentucky 40512  
(859) 269-2351

Request a Quote

## REPORT DATA

Report Number: KK2214

### NSF STANDARD 51 COMPOUND

<u>N1219-60</u>	<u>Production Limits</u>	<u>Typical Data</u>
Hardness	60 ± 5	62
Tensile	1800 min	2100
Elongation	400 min	525
Specific Gravity	1.26 (±.02)	1.26