



Request a Quote

Compound Data Sheet  
Parker O-Ring Division United States

# MATERIAL REPORT

REPORT NUMBER:

DATE: 1/19/2000

**TITLE:** Evaluation of Parker Compound VA151-75 (19357)

**PURPOSE:** To obtain general information

Recommended temperature limits: -15<sup>0</sup>F to 400<sup>0</sup>F

Recommended For

Petroleum, mineral, and vegetable oils  
Silicone fluids  
Aromatic hydrocarbons (benzene, toluene)  
Chlorinated hydrocarbons  
High vacuum  
Ozone, weather, aging resistance

Not Recommended For

Hot water and steam  
Auto and aircraft brake fluids  
Amines  
Ketones  
Low molecular weight esters and ethers

Parker O-Ring Division  
2360 Palumbo Drive  
Lexington, Kentucky 40509  
(859) 269-2351



## REPORT DATA

	<b>Test Results</b>
<b>Original Physical Properties, ASTM D1414, D2240</b>	
Tensile Strength, psi	1510
Ultimate Elongation, %	167
Modulus @ 100%, psi	778
<b>Compression Set, ASTM D395 Method B (70 hrs. @ 392°F)</b>	
Percent of Original Deflection	23
<b>Compression Set, ASTM D395 Method B (336 hrs. @ 392°F)</b>	
Percent of Original Deflection	46
<b>Dry Heat Resistance, ASTM D573 (168 hrs. @ 480°F)</b>	
Hardness Change, pts.	+4
Tensile Change, %	-1
Elongation Change, %	-15
<b>Dry Heat Resistance, ASTM D573 (168 hrs. @ 527°F)</b>	
Hardness Change, pts.	+12
Tensile Change, %	-34
Elongation Change, %	-55
<b>Fluid Immersion, ASTM D471 Fuel B, (70 hrs. @ 73°F)</b>	
Hardness Change, pts.	-4
Tensile Change, %	-10
Elongation Change, %	-1
Volume Change, %	+1
<b>Fluid Immersion, ASTM D471 AMS 3023, (70 hrs. @ 392°F)</b>	
Hardness Change, pts.	-8
Tensile Change, %	-25
Elongation Change, %	-4
Volume Change, %	+17
<b>Fluid Immersion, ASTM D471 IRM 903 Oil, (70 hrs. @ 302°F)</b>	
Hardness Change, pts.	-3
Tensile Change, %	-5
Elongation Change, %	+1
Volume Change, %	+2