



Marco Compound # S1057

60 Durometer, Orange, High Temperature Silicone

Technical Datasheet

Common Names:

Silicone, VQM

General Description:

Silicones are excellent seal materials for extreme temperature in static applications. Silicones can be synthesized with a wide variety of properties and compositions. Please contact engineering@marcorubber.com for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

Features:

- Compliant to A-A-59588 CL 2A & 2B
- High Temperature
- Excellent heat and compression resistance
- Excellent resistance to oxygen, ozone and sunlight
- Good chemical resistance
- Resistance to fungal and biological attack
- Flexible
- Good electrical insulation

Limitations:

- Not recommended for dynamic application
- Concentrated solvents, oils, concentrated acids, diluted sodium hydroxide.
- Poor abrasion resistance
- Low strength
- High gas permeability

Service Temperature:

-65 to 600° F (-55 to 315° C)

Specification:

ASTM 2000 M5GE606 A19 B37 EO16 EO36 Z1 (Z1 = High Temp.)

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	ASTM D2000 Requirements	Typical Test Results
Hardness, Shore A	60 +/- 5	59
Color	Orange	Orange
Tensile Strength, MPa (psi)	6.0 (870)	8.5 (1232)
Ultimate Elongation, %	200	328
Specific Gravity	-----	1.213

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

HEAT RESISTANCE – A19, ASTM D 573 (70 hrs. @ 225°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A	+10	+3
Tensile Strength Change, %, max.	-25	-9
Ultimate Elongation Change, %, max.	-30	-19

COMPRESSION SET – B37, ASTM D 325 Method B (22 hrs. @ 175°C)	ASTM D2000 Requirements	Typical Test Results
Permanent Set, %, max.	25	15
Heat aging at 150° C x 70 hrs.	--	9

FLUID RESISTANCE –ASTM #1 Oil – EO36, ASTM D 471 (70 hrs. @ 150°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A	0 to -15	-8
Tensile Strength Change, %, max.	-20	-4
Ultimate Elongation Change, %, max.	-20	-5
Volume Change, %	0 to +10	+8

FLUID RESISTANCE – IRM 903 Oil, -EO36, ASTM D 471 (70 hrs. @ 150°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A, max.	-30	-22
Volume Change, %, max.	+ 60	+48

Date: 2015-11-10