

(800) 775-6525 Fax: (800) 421-2923 <u>engineering@marcorubber.com</u> www.marcorubber.com



## ΩHMERICS Compound# S1134 Pure Silver Filled Silicone EMI RFI Shielding Conductive Elastomer

This compound provides very high shielding effectiveness but is susceptible to corrosion. This material should not be used in tropical environments. Please contact <a href="mailto:engineering@marcorubber.com">engineering@marcorubber.com</a> for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

## Features:

- High Shielding effectiveness
- Excellent moisture seal
- Many profiles and shapes are available
- Generally used for low closure force applications

## Limitations:

- Material will have corrosion in a salt air environment
- Poor abrasion resistance
- Not to be used in an NBC washdown

## TYPICAL PHYSICAL PROPERTIES

Typical Use or Specification	MIL-DTL 83528 Type J	
Elastomer Binder	Silicone	
Conductive Filler	Pure Silver	
Color	Tan	
ORIGINAL PROPERTIES	Test Procedure	Typical Value
Durometer, Shore A	ASTM D2240	45
Tensile Strength, Min., psi	ASTM D412	150
Ultimate Elongation, Min., %	ASTM D412	100
Specific Gravity, ASTM D297	ASTM D792	1.8
Compression Set, % (70 hrs. @ 100°C)	ASTM D395	35
Compression/Deflection %	ASTM D575	8.0
Tear Strength, Min., lbs/in	ASTM D624	20
Operating Temperature Range °C	ASTM D1329	-55 to +160
Volume Resistivity, Ohm-cm	Mil-DTL 83528	0.010
Shielding Effectiveness, ASTM D4935, 100 MHz-10 GHz (E-field) db	Mil-DTL 83528	90

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.