

(800) 775-6525 Fax: (800) 421-2923 engineering@marcorubber.com www.marcorubber.com

Marco Compound # S1167 70 Durometer, Orange, Silicone Compliant to ZZ-R-765, CL-2B, GR-70 Technical Datasheet

Common Names:

Silicone, VQM

General Description:

Silicones are excellent seal materials for extreme temperature in static applications. Silicones can be synthesized with a wide variety of properties and compositions. Please contact <u>engineering@marcorubber.com</u> for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

Features:

- High Temperature
- Compliant to ZZ-R-765, CI-2B, Gr-70
- Excellent heat and compression resistance
- Excellent resistance to oxygen, ozone and sunlight
- Good chemical resistance
- Resistance to fungal and biological attack
- Flexible
- Good electrical insulation
- FDA compliant per 21CFR177.2600

Limitations:

- Not recommended for dynamic application
- Concentrated solvents, oils, concentrated acids, diluted sodium hydroxide.
- Poor abrasion resistance
- Low strength
- High gas permeability

Service Temperature:

-65 to 600° F (-54 to 315° C)

Specification:

ASTM 2000 M5GE706 A19 B37 EO16 EO36 Z1 (Z1 = High Temp.)

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	ASTM D2000	Typical Test
	Requirements	Results
Hardness, Shore A	70 +/- 5	69
Color	Orange	Orange
Tensile Strength, psi	865	940
Ultimate Elongation, %	150	220
Specific Gravity		1.18

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

Request a Quote

HEAT RESISTANCE – A19, ASTM D 573 (70 hrs. @ 225°C)	ASTM D2000	Typical Test
	Requirements	Results
Hardness Change, points, Shore A	+10	+5
Tensile Strength Change, %, max.	-25	+1
Ultimate Elongation Change, %, max.	-30	-6

COMPRESSION SET – B37, ASTM D 325 Method B (22 hrs. @ 175°C)	ASTM D2000 Requirements	Typical Test Results
Permanent Set, %, max.	25	20

FLUID RESISTANCE -ASTM #1 Oil - EO36, ASTM D 471 (70 hrs. @ 150°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A	0 to -15	-5
Tensile Strength Change, %, max.	-20	-14
Ultimate Elongation Change, %, max.	-20	+1
Volume Change, %	0 to +10	+2

FLUID RESISTANCE – IRM 903 OII, -EO36, ASTM D 471 (70 hrs. @ 150°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A, max.	-30	-19
Volume Change, %, max.	+ 60	+13

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.