

(800) 775-6525 Fax: (800) 421-2923 <u>engineering@marcorubber.com</u> www.marcorubber.com

# Marco Compound # S1188 70 Durometer, White, Platinum Cured, USP Class VI Silicone Technical Datasheet

### **Common Names:**

Silicone, VQM

#### **General Description:**

Silicones are excellent seal materials for extreme temperature in static applications. Silicones can be synthesized with a wide variety of properties and compositions. Marco compound S1188 is platinum cured and USP Class VI compliant for use in pharma applications. Please contact <a href="mailto:engineering@marcorubber.com">engineering@marcorubber.com</a> for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

# Features:

- Platinum cured
- USP Class VI compliant
- Standard manufacturing (not clean room manufactured)
- Excellent heat and compression resistance
- Excellent resistance to oxygen, ozone and sunlight
- Good chemical resistance
- Resistance to fungal and biological attack
- Flexible
- Good electrical insulation

#### **Limitations**:

- Not recommended for dynamic application
- Concentrated solvents, oils, concentrated acids, diluted sodium hydroxide.
- Poor abrasion resistance
- Low strength
- High gas permeability

# **Cure System:**

Platinum

#### Service Temperature:

-65 to 400° F (-54 to 205° C)

# **TYPICAL PHYSICAL PROPERTIES**

ORIGINAL PROPERTIES	Typical Test Results
Hardness, Shore A	70
Color	White
Tensile Strength, psi	650
Ultimate Elongation, %	125

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

# Request a Quote

COMPRESSION SET – ASTM D 325 Method B (22 hrs. @ 175°C)	Typical Test Results
Permanent Set, %, max.	19

LOW TEMPERATURE RESISTANCE – ASTM D 2137 Method A, 9.3.2	Typical Test Results
Non-brittle after 3 min. @ -55° C	Pass

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.