

## Material Properties: Simriz® 487 (FFKM)

NOTE - All testing done on AS568-214 size O-rings

Original Properties	Simriz 487
Color	Black
Hardness, Shore A, ASTM D2240	79
Tensile Strength, MPa, ASTM D412 Die C	18.7
Tensile Strength, psi, ASTM D412 Die C	2710
% Elongation change, ASTM D412 Die C	170
100% Modulus, Mpa, ASTM D412 Die C	8.6
100% Modulus, psi, ASTM D412 Die C	1245
<b>Low Temperature Glass Transition Temperature, ASTM D3418</b>	
Tg (degrees C)	0
<b>Low Temperature Retraction, ASTM D1329</b>	
TR-10, degrees C	0
<b>Air Aging ASTM D573, 70 hrs. at 250°C</b>	
Hardness change, Shore A, ASTM D2240	0
% Tensile Strength change, ASTM D1414	-13
% Elongation change, ASTM D1414	+24
% Weight loss, ASTM D573	1.0
<b>Compression Set, ASTM D395 Method B and ASTM D1414</b>	
% Permanent Set, 70 hrs. at 275°C	26
% Permanent Set, 300 hrs. at 275°C	44
% Permanent Set, 70 hrs. at 300°C	29
% Permanent Set, 300 hrs. at 300°C	43
<b>Water Bomb Fluid Immersion, ASTM D471, 70 hrs. at 200°C</b>	
% Volume change, ASTM D471	+1.9

© Copyright 2013

The information contained herein is believed to be reliable, but no representation, guarantees or warranties of any kind are made to its accuracy or suitability for any purpose. The information presented herein is based on laboratory testing and does not necessarily indicate end product performance. Full scale testing and end product performance are the responsibility of the user.

[www.simrit.com](http://www.simrit.com)  
 866-274-6748