

Marco Compound # V1000

75 Durometer, Black, Commercial Grade FKM

Technical Datasheet

Common Names:

FKM, Fluoropolymer, Fluorel®, Viton®,

General Description:

FKM compounds are widely used in chemical, automotive, aerospace and industrial applications. These compounds offer excellent chemical and temperature resistance. V1000 is Marco's basic commercial grade compound. There are many additional specialty compounds based on A, B, F, GLT, GFLT, LTFE and ETP polymer types. Please contact sales@marcorubber.com for assistance in selecting a specialized compound when increased resistance to temperature, chemicals, or physical properties is required.

Features:

- High temperature resistance.
- Excellent resistance to acids, fuels, mineral oils, greases, aliphatic, aromatic and chlorinated hydrocarbons, non-flammable hydraulic fluids (HFD) and many organic solvents and chemicals.
- Excellent resistance to aging and ozone.
- Low gas permeability, low compression set.

Limitations:

- Steam, hot water, amines, polar solvents, low molecular weight organic solvents and glycol-based brake fluids.

Cure System:

Bisphenol

Service Temperature:

-15 to 437°F

(Additional compounds may be available with expanded temperature ranges).

Specification:

ASTM 2000 M4HK710 A1-11 B38 EF31 EO31 EO78 Z1

PHYSICAL PROPERTIES

ORIGINAL PROPERTIES	ASTM D2000 Requirements	Typical Test Results
Hardness, Shore A, ASTM D2240 (Z1=75+/-5)	75 +/- 5	75
Color	Black	Black
Tensile Strength, MPa (psi), per ASTM D412	10.0 (1,450) min.	11.5 (1,650)
Ultimate Elongation, %, per ASTM D412	175 Min.	200

HEAT RESISTANCE – A1-11, ASTM D 573 (70 hrs. @ 275°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+10 (max)	+5
Tensile Strength Change, %, ASTM D412	-40 (max)	-13
Ultimate Elongation Change, %, ASTM D412	-25 (max)	-20

COMPRESSION SET – B38, ASTM D 395 Method B (22 hrs. @ 200°C)	ASTM D2000 Requirements	Typical Test Results
Permanent Set %	50 (max)	20

FLUID RESISTANCE – ASTM Fuel C – EF31, ASTM D 471(70 hrs. @ 23°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+/- 10	-4
Tensile Strength Change, %, ASTM D412	-25 (max)	-20
Ultimate Elongation Change, %, ASTM D412	-20 (max)	-13
Volume Change, %, ASTM D471	0 to + 10	+4

FLUID RESISTANCE –ASTM #101 Oil – EO78, ASTM D 471 (70 hrs. @ 200°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	-15 to + 5	-10
Tensile Strength Change, %, ASTM D412	-40 (max)	-15
Ultimate Elongation Change, %, ASTM D412	-20 (max)	-7
Volume Change, %, ASTM D412	0 to + 15	14

Date: 2016-5-10

Viton® is a registered trademark of Dupont.

Fluorel® is a registered trademark of Dyneon.