



## Marco Compound # V1001

### 50 Durometer, Brown Commercial grade FKM

### Technical Datasheet

#### Common Names:

FKM, Fluoropolymer, Fluorel®, Viton®

#### General Description:

FKM compounds are widely used in chemical, automotive, aerospace and industrial applications. These compounds offer excellent chemical and temperature resistance. Brown Viton can provide improved resistance to oxidative environments and reactive plasmas. There are many additional specialty compounds based on A, B, F, GLT, GFLT, LTFE and ETP polymer types. Please contact [engineering@marcorubber.com](mailto:engineering@marcorubber.com) for assistance in selecting a specialized compound when increased resistance to temperature, chemicals, or physical properties is required.

#### Features:

- High temperature resistance.
- Excellent resistance to acids, fuels, mineral oils, greases, aliphatic, aromatic and chlorinated hydrocarbons, non-flammable hydraulic fluids (HFD) and many organic solvents and chemicals.
- Excellent resistance to aging and ozone.
- Low gas permeability, low compression set.

#### Limitations:

- Steam, hot water, polar solvents, low molecular weight organic solvents and glycol-based brake fluids.

#### Cure System:

Bisphenol

#### Service Temperature:

-15 to 400°F

(Additional compounds may be available with expanded temperature ranges).

#### Specification:

ASTM 2000 M2HK507 A1-10 B37 EF31

### PHYSICAL PROPERTIES

ORIGINAL PROPERTIES	ASTM D2000 Requirements	Typical Test Results
Hardness, Shore A, ASTM D2240 (Z1=75+/-5)	50 +/- 5	55
Color	Brown	Brown
Tensile Strength, MPa (psi), ASTM D412	7.0 (1,000) min.	7.0 (1,000)
Ultimate Elongation, %, ASTM D412	200 Min.	310
Specific Gravity		1.93

This information is to the best of our knowledge accurate and reliable. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

HEAT RESISTANCE – A1-10, ASTM D 573 (70 hrs. @ 250°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+10 (max)	+3
Tensile Strength Change, %, ASTM D412	-25 (max)	-7
Ultimate Elongation Change, %, ASTM D412	-25 (max)	-3

COMPRESSION SET – B37, ASTM D 395 Method B (22 hrs. @ 200°C)	ASTM D2000 Requirements	Typical Test Results
Permanent Set %	50 (max)	8

FLUID RESISTANCE – ASTM Fuel C – EF31, ASTM D 471(70 hrs. @ 23°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+/- 5	-2
Tensile Strength Change, %, ASTM D412	-25 (max)	-10
Ultimate Elongation Change, %, ASTM D412	-20 (max)	-16
Volume Change, %, ASTM D471	0 to + 10	+ 2

Viton® is a registered trademark of Dupont.

Fluorel® is a registered trademark of Dyneon.